

# MONTOTHERM PRIMER



## FAMILY

REVESTIMIENTOS DE FACHADAS

## LINE

ESPECIFICOS/MORTEROS MONOCAPA

## DESCRIPTION AND NATURE

Water-based paint used for priming the reinforcing layer prior to application of plastering mortar for the MONTOTHERM system. This product contributes to LEED®, BREEAM® and VERDE certifications.

## USAGES

Outdoor

Monto Thêrm Adhesive Mortar

Preparation and priming of Monto Thêrm system reinforcement layer,

## PROPERTIES

Adherence

Does not spread flame

Elasticity enough to resist the normal structural movements

Excellent covering

Good applicability

Superior waterproofing and breathability



## TECHNICAL CHARACTERISTICS

Referencia Color	MONTOTHERM PRIMER BLANCO
Finish	Smooth matt
Specific weight	1,53± 0,05 kg/l
Viscosity	120 +/- 20 PO
Solids in volume	43± 1
Solids in weight	64± 1
VOC	Cat. c/BA 75/40 (2007/2010): 1,89 g/l
Aproximated performance by coat	6-9 m²/L

Dry to touch	(20°C HR: 60%): 30-60min
Dry to repaint	(20°C HR: 60%): 6h
Colours	White and colors MONTOTHERM Eterna chart

## SURFACE PREPAIRING

### New surfaces

MONTOTHERM system reinforcement layer:

1. Wait until it has completely set (at least 28 days).
2. Clean the surface of possible substances that may reduce adhesion.



Fecha de Alta

12-12-2011

Versión

5 - 14/08/2024

3. Apply to dry surfaces.

**Restoring and maintenance**

## WAY OF USE

### Application notes

Stir the product until perfectly blended.

- Dilute the product according to the porosity and state of the base on the first coat.
- Finish with one or two coats of slightly diluted MONTOTHERM Primer, until the whole of the base is covered.
- Do not apply the product at temperatures below 5°C or on surfaces exposed to strong insolation.

### Solvent for dilution and cleaning

Water

Way of use	Aproximate dilution
Painting brush	10-20%
Roller	10-20%
Spray gun	10-30%

## SYSTEM

### Procedures depending of surface type

	Primer	Intermedium	Finish
<b>Reinforce coat from MONTOTHERM system</b>			
<b>MAX</b>	MONTOTHERM Primer diluido	MONTOTHERM Primer	MONTOTHERM Mortero Acilico 70, MONTOTHERM Mortero Acilico 120 ó MONTOTHERM Mortero Siloxano 120
<b>STD</b>			

## SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in fire. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

## NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to establish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

## PACKINGS

15 L