

PLASMONT BRICOLAGE CEMENTO BLANCO



FAMILY LINE

PREPARACIONES, FONDOS E IMPR.
MASILLAS EN POLVO

DESCRIPTION AND NATURE

With cement powder. Excellent for repairing and rejoining where white finish is required.

USAGES

Outdoors/Indoors
Plaster finishing

PROPERTIES

Strongness
High and medium thickness finishings
Good adhesion
Fast hardening
Smooth touch

TECHNICAL CHARACTERISTICS

Referencia Color	PLASMONT BRICOLAGE CEMENTO BLANCO
Mixture relation	375 ml de agua por kg de masilla
Finish	Matt
Specific weight	2,91± 0,05 kg/l
Solids in volume	100± 1
Solids in weight	100± 1
Aproximated performance by coat	Depending of product usage

Dry to touch	(20°C HR: 60%): 2h
Dry to repaint	(20°C HR: 60%): 24h
Colours	White

SURFACE PREPAIRING

New surfaces

Plaster and mortar cement:

- Test CEMENTO BLANCO suitability on surface.
- Wait till complet drying of product before top coat.
- Remove off any efflorescences through abrassive jet and neutralize alkaline surfaces.
- Extremely polished surfaces should be treated to open pores.
- Remove off any foreing products or remains.
- Open any fissures or cracks until obtaining good condition surface. Remove off any resulting dust by brushing and apply CEMENTO BLANCO as indicated under Application Systems and Application points.
- For extremely damaged surfaces, use suitable fixer (see family 6) .

Restoring and maintenance

Remove off any remains or peeling of paint or any other foreign products. Open pore by sandpapering or any other

PLASMONT BRICOLAGE CEMENTO BLANCO

mechanical systems.

Test adherence level and treat as per new surfaces.

WAY OF USE

Application notes

-For its thinning, use only fresh, clean water.

-Use only indicated tools under "Application Systems", clean and rust-free.

-Bad condition surfaces should be anchored with Fijamont, Emulsión Fijadora or Fijalite.

-Repaint once the indicated time has passed. As this depends on the moisture levels, temperature and thickness of the layer, if the sandpaper does not stick this will tell us that the product is ready to proceed.

Solvent for dilution and cleaning

Way of use

Stainless trowel

Pallette / spatula

Pallette

Aproximate dilution

375 ml de agua por kg de masilla

375 ml de agua por kg de masilla

375 ml de agua por kg de masilla

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Project			
MAX	Cemento blanco	Fijador (Emulsión Fijadora, Fijamont)	Familia 1, 2 y 4
STD			

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in drain. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in drain. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE


Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to establish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

1.5 Kg

PLASMONT BRICOLAGE CEMENTO BLANCO



FAMILY LINE

DESCRIPTION AND NATURE

With cement powder. Excellent for repairing and rejoining where white finish is required.

USAGES

PROPERTIES

Strongness
High and medium thickness finishings
Good adhesion
Fast hardening
Smooth touch

TECHNICAL CHARACTERISTICS

Referencia Color	
Mixture relation	375 ml de agua por kg de masilla
Finish	Matt
Specific weight	2,91± 0,05 kg/l
Solids in volume	100± 1
Solids in weight	100± 1
Aproximated performance by coat	Depending of product usage
Dry to touch	(20°C HR: 60%): 2h
Dry to repaint	(20°C HR: 60%): 24h
Colours	White

SURFACE PREPAIRING

New surfaces


Plaster and mortar cement:

- Test CEMENTO BLANCO suitability on surface.
- Wait till complet drying of product before top coat.
- Remove off any efflorescences through abrassive jet and neutralize alkaline surfaces.
- Extremely polished surfaces should be treated to open pores.
- Remove off any foreing products or remains.
- Open any fissures or cracks until obtaining good condition surface. Remove off any resulting dust by brushing and apply CEMENTO BLANCO as indicated under Application Systems and Application points.
- For extremely damaged surfaces, use suitable fixer (see family 6) .

Restoring and maintenance

Remove off any remains or peeling of paint or any other foreign products. Open pore by sandpapering or any other mechanical systems.
Test adherence level and treat as per new surfaces.

PLASMONT BRICOLAGE CEMENTO BLANCO



WAY OF USE

Application notes

-For its thinning, use only fresh, clean water.

-Use only indicated tools under "Application Systems", clean and rust-free.

-Bad condition surfaces should be anchored with Fijamont, Emulsión Fijadora or Fijalite.

-Repaint once the indicated time has passed. As this depends on the moisture levels, temperature and thickness of the layer, if the sandpaper does not stick this will tell us that the product is ready to proceed.

Solvent for dilution and cleaning

Way of use

Stainless trowel

Pallette / spatula

Pallette

Aproximate dilution

375 ml de agua por kg de masilla

375 ml de agua por kg de masilla

375 ml de agua por kg de masilla

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Project			
MAX	Cemento blanco	Fijador (Emulsión Fijadora, Fijamont)	Familia 1, 2 y4
STD			

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

PACKINGS

1.5 Kg