

Fecha de Alta

30-10-2008

Versión

7 - 19/08/2024



FAMILY MADERA

LINE ACEITES

DESCRIPTION AND NATURE

Mix of natural oils for nourishing and protecting wood without varnishing.

USAGES

Outdoors/Indoors

Wood

Use for general public

PROPERTIES

Optimal applicability
 Penetration power
 No sanding necessary for repainting. Non expensive maintenance
 Protective for fungus and bacterials
 Doesn't film build
 Endures brusque changes in the weather
 Reinforced with U.V. filter

TECHNICAL CHARACTERISTICS

Referencia Color	ACEITE DE TECA
Finish	Transparent
Specific weight	0,81 ± 0,05 kg/l
Solids in volume	49 ± 1
Solids in weight	53 ± 1
Aproximated performance by coat	10-20 m ² /L

Dry to touch	(20°C HR: 60%): 24-48h
Dry to repaint	(20°C HR: 60%): > 30min
Colours	Honey

SURFACE PREPAIRING**New surfaces**

New woods:

- The support must be free of foreign products and/or residues.
- Apply to wood with a moisture content of less than 20%.
- Apply to healthy, well-degreased, dust-free and dry wood.
- Sand and eliminate possible traces of glue in the assemblies and machining errors.
- If the wood shows signs of aging, it must be previously sanded and dust removed by brushing or any other mechanical means.
- By spray, the most recommended means of application is the Airless System.

Restoring and maintenance

Varnished or painted wood:

- If they have been varnished with Montoxyl Color, remove foreign products, eliminate poorly adhered areas or areas in poor condition, sand lightly, eliminate the dust resulting from sanding and proceed as with new wood.
- If they have been varnished with closed-pore varnishes such as Synthetic or Similar Varnishes, remove by stripping with Quitamont Universal or by mechanical means and proceed as with new wood.

Fecha de Alta

30-10-2008

Versión

7 - 19/08/2024

WAY OF USE

Application notes

Remove remains of foreign products, grease, dirt or remains of closed-pore varnishes.

To remove grease and most dirt, wash with detergent in water and let dry.

To remove paints or varnishes, strip or use mechanical means.

Stir the product until it is perfectly homogenized.

Pre-sanding with fine sandpaper is always advisable.

Apply liberally, preferably with a brush or roller, leaving excess product.

Let about 30 minutes pass and remove the excess with a cloth that does not leave threads and repaint.

For exquisite finishes, allow at least 4 hours between coats and sand.

Later give a second hand.

Do not apply the product at high temperatures, or on surfaces exposed to strong sunlight.

Maintain good ventilation conditions during drying time.

Do not apply with relative humidity greater than 80%.

Solvent for dilution and cleaning

Solvent 1401

Way of use	Aproximate dilution
Painting brush	0
Roller	0
Air-less gun	0
Air-mix gun	0
Aerographic gun	0
Low pressure turbo	0

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Painted or varnished wood (closed pore) outdoor			
MAX	Eliminar totalmente, Lijado + Aceite de Teca	Lijado + Aceite de Teca	Lijado + Aceite de Teca
STD	Eliminar totalmente, Lijado + Aceite de Teca		Aceite de Teca
New /old wood indoor/outdoor			
MAX	Lijado+Aceite de Teca	Lijado+Aceite de Teca	Lijado+Aceite de Teca
STD	Aceite de Teca		Aceite de Teca
Open pore varnished wood			
MAX	Lijado+Aceite de Teca	Lijado+Aceite de Teca	Lijado+Aceite de Teca
STD	Aceite de Teca		Aceite de Teca

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Fecha de Alta

30-10-2008

Versión

7 - 19/08/2024

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to establish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

0.75 L, 5 L