



FAMILY MADERA / SISTEMAS TINTOMÉTRICOS

LINE PROTECTORES (AGUA)

DESCRIPTION AND NATURE

Protective lasur for water-based wood, with UV filter. Open pore treatment with easy maintenance, generates a protective and breathable elastic film, with excellent weather resistance.

USAGES

Outdoors/Indoors

For maximum protection, finish in colour.

Recommended previously created with primer

Specially recommended for mountain and coastal areas

PROPERTIES

Penetration power

Provides open pore finish

Do not apply white media, you can amarillearlos slightly, but does not alter the properties of the product.

Non Yellowing

No need of sanding, but easy to do once dried

Recommended number of coats : 2-3 coats over new wood, 1-2 coats as maintenance

No cracking at all

Does not form blisters

Water steam transpirable

Odourless when dry

Endures brusque changes in the weather

Flexible

Microporous

Highlights the wood's natural grain

U.V. resistant

May be used as a base when diluted, thus nourishing the wood

TECHNICAL CHARACTERISTICS

| | |
|---------------------------------|---|
| Referencia Color | MONTOXYL LASURE ACQUA SATINADO |
| Finish | Satin |
| Specific weight | 0,98± 0,05 kg/l |
| Viscosity | 8 +/- 2 PO |
| Solids in volume | 20± 1 |
| Solids in weight | 22± 1 |
| VOC | Cat. e/BA 150/130 (2007/2010):5,05 g/l |
| Aproximated performance by coat | 10-16 m²/L |
| Dry to touch | (20°C HR: 60%): 2-4h |
| Dry to repaint | (20°C HR: 60%): 12-24h |
| Colours | Base: TR 900 Montoxyl and Wood 100 charts. Montomix (max 5%) systems. |
| Classification | Cumple con la NORMA UNE 23727-90 1ª R / REACTION FEU M1 |

SURFACE PREPAIRING

######

MONTOXYL LASURE ACQUA SATINADO

**New wood/old outdoor**

| | | | |
|------------|--------------------------|----------------------|-----------------------------|
| MAX | Anticarcomas Klearxyl Di | Montoxyl Fondo Color | Lasure Acqua Satinado Color |
| STD | Anticarcomas Klearxyl Di | | Lasure Acqua Satinado Color |

Old/New interior Wood

| | | | |
|------------|-------------------------------|----------------|-----------------------|
| MAX | Lasure Acqua o Montoxyl Fondo | Montoxyl Fondo | Lasure Acqua Satinado |
| STD | Lasure Acqua o Montoxyl Fondo | | Lasure Acqua Satinado |

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in drain. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to establish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

0.75 L, 4 L