

Fecha de Alta

13-08-2019

Versión

7 - 12/08/2024



FAMILY PAREDES Y TECHOS
LINE MONTOPLAC

DESCRIPTION AND NATURE

Ideal painting for direct decoration of Laminate Plate (PYL). It facilitates professional application, reducing the number of layers needed to cover joints and putty, as well as helping to disguise the translucent. Ideal as finishing paint in Q2 and Q3 installations. This product contributes to LEED®, BREEAM® and VERDE certifications.

USAGES

Inside
 Walls and ceilings
 Drywall (gypsum plasterboard)
 Other supports can also be applied such as plaster, cast cast, cement, brick...

PROPERTIES



Gloss level: matt (according to UNE-EN 13300, at 85° reflectance < 10)

Washability: Class 3 (according to Standard UNE-EN 13300)

Opacity: Class 1 for a performance of 6,5 m²/litre (according to Standard UNE-EN 13300)

With anti-mould additive



TECHNICAL CHARACTERISTICS

| | |
|---------------------------------|---------------------------------------|
| Referencia Color | MONTOPLAC MATE BLANCA |
| Finish | . |
| Specific weight | 1,49± 0,05 kg/l |
| Viscosity | 70 +/- 10 PO |
| Solids in volume | 39± 1 |
| Solids in weight | 61± 1 |
| VOC | Cat. a/BA 75/30 (2007/2010): 1,59 g/l |
| Aproximated performance by coat | 12-14 m ² /L |
| Dry to touch | (20°C HR: 60%): 1h |
| Dry to repaint | (20°C HR: 60%): 4-6h |
| Colours | White |

SURFACE PREPAIRING

Fecha de Alta

13-08-2019

Versión

7 - 12/08/2024

New surfaces

Plasterboard partition walls:

1. Carry out a general sanding of the joints and putty fixing areas.
2. Then, clean them to ensure the substrate is free of dust, grease and other contaminants.
3. For application on coloured boards that tend to generate stains, apply Montoplac Sellador Antimanchas.

Cement and concrete mortars:

1. Wait until fully set (min. 30 days).
2. Clean any efflorescence with a jet washer.
3. Neutralize alkaline surfaces.
4. Sand polished surfaces to create a rougher surface.
5. Clean the surface to remove foreign products.
6. Set crumbly substrates with Fixer Emulsion or Fijamont.
7. Fill in defects in the substrate (see family 6)

Plaster, plaster-covered brick:

1. Wait until it is completely dry (max. 20% humidity).
2. Clean the surface to remove foreign products.
3. Clean any efflorescence with a jet washer.
4. Regulate surface absorption with sealer, fixer, or a diluted coat of the same product
5. Sand polished surfaces to create a rougher surface
6. Set crumbly substrates with Fixer Emulsion or Fijamont.
7. Fill in defects in the substrate (see family 6)

Restoring and maintenance

1. Completely remove old paint that is in poor condition or that is poorly-adhered.
2. Glossy surfaces should be thinned out to ensure good adhesion.
3. On painted surfaces, check that the paint is solid and well-adhered. Its condition must be assessed, in order to avoid possible incompatibilities. Dust and dirt must also be eliminated before repainting.
4. Apply filler (Plasmont) to any defects on the surface.
5. Pre-treat mouldy walls using Monto Limpia Moho.

WAY OF USE**Application notes**

- Shake the product until perfect homogenisation.
- Dilute the product according to the porosity and condition of the support in the first layer.
- Finish with one or more slightly diluted layers until full covering of the support.
- Do not apply the product at temperatures below 5 °C or on surfaces exposed to severe sunshine.
- Do not wash until after 24 days.
- Clean the tools with water immediately after use.
- For projection with Airless equipment, use 15 to 23 inch step nozzles, pressure 150 bar.

Solvent for dilution and cleaning

Water

| Way of use | Aproximate dilution |
|----------------|---------------------|
| Painting brush | Máx. 5% |
| Roller | Máx. 5% |
| Air-less gun | 5% |

SYSTEM**Procedures depending of surface type**

| | Primer | Intermedium | Finish |
|--------------------------------------|------------------------|------------------------|------------------------|
| Drywall (gypsum plasterboard) | | | |
| MAX | Montoplac Pintura Mate | Montoplac Pintura Mate | Montoplac Pintura Mate |
| STD | Montoplac Pintura Mate | | Montoplac Pintura Mate |

Fecha de Alta

13-08-2019

Versión

7 - 12/08/2024

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in drain. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to establish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

15 L