

Fecha de Alta

08-08-2006

Versión

5 - 20/05/2024



FAMILY

PREPARACIONES, FONDOS E IMPR.

LINE

MASILLAS EN POLVO

DESCRIPTION AND NATURE

Universal powdered filler for filling holes, refilling major defects, smoothing minor imperfections and finishing

USAGES

Indoors
Cement
Plaster
Wood
Concrete
Plaster

PROPERTIES

High and medium thickness finishings
fast hardening
Smooth rugged touch
Easy mixing
Do not come in clots

TECHNICAL CHARACTERISTICS

Referencia Color	PLASMONT MULTIUSO
Mixture relation	450-550 ml de agua por kg masilla
Finish	Matt
Specific weight	2,42± 0,05 kg/l
Solids in volume	100± 1
Solids in weight	100± 1
Aproximated performance by coat	Depending of product usage
Dry to touch	(20°C HR: 60%): 4-5h
Dry to repaint	(20°C HR: 60%): 24-48h
Colours	White

SURFACE PREPAIRING

New surfaces

*-Cement / plaster mortar: Check suitability of PLASMONT MULTIUSO STANDARD on surface. -Allow to harden completely (minimum 30 days) -Remove possible efflorescence and neutralise alkaline surfaces. -Sand to open the pores of excessively polished surfaces.

-Remove external products and/or residues. -Back gouge any cracks or fissures down to repaired base, remove subsequent dust with brush and apply PLASMONT MULTIUSO STANDARD filler as instructed in the Application Systems and Applications. -Do not exceed the maximum recommended thickness of coats. - On surfaces in an excessively poor condition suitable fixative should be used before applying filler (see product family 6).

-Wood: -Check suitability of PLASMONT MULTIUSO STANDARD on surface. - Sand to open pores of excessively polished surfaces. -Remove external products and/or residues.

-Back gouge any cracks or fissures down to repaired base, remove subsequent dust with brush and apply PLASMONT MULTIUSO STANDARD filler as instructed in the Application Systems and Applications. -Do not exceed the maximum recommended thickness of coats. -Apply on healthy, grease-free, resin free, dust free and dry wood with less than 20% internal dampness. If the wood shows signs of ageing it should be sanded and the cracks back gouged to healthy wood.

Fecha de Alta

08-08-2006

Versión

5 - 20/05/2024

Restoring and maintenance

Remove off any remains or chipping of product or any other foreign product. Open pore by sandpápering or any other mechanical systems. Test adherence level and treat as per new surfaces.

WAY OF USE**Application notes**

Dilute with clean, unpolluted water.

Use the tools indicated in the application system instructions. Ensure the tools are clean, in good working order and of course, rust free.

Repaint following the indicated period of time. Given that this depends on the levels of humidity, temperature and thickness of the coating, the lack of clogging of the sandpaper with indicate that the product is ready for repainting.

Solvent for dilution and cleaning

Water

Way of use

Stainless trowel

Palette / spatula

Palette

Aproximate dilution

450-550 ml agua/kg masilla

450-550 ml de agua/kg masilla

450-550 ml de agua/kg masilla

SYSTEM**Procedures depending of surface type**

	Primer	Intermedium	Finish
Wood			
MAX	Selladora sellalux	Selladora sellalux	Fijador+Montoplástica o Familia 4
STD	Plasmont Multiusos Standar		Montoplástica o Familia 4
Project			
MAX	Fijador (Emulsión Fijadora Fijamont)	Plasmont Multiusos Standar	Fijador+Montoplástica, Familia 4
STD	Plasmont Multiusos Standar		Montoplástica, Familia 4

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

1 Kg, 5 Kg, 15 Kg



FAMILY LINE

DESCRIPTION AND NATURE

Universal powdered filler for filling holes, refilling major defects, smoothing minor imperfections and finishing

USAGES

PROPERTIES

High and medium thickness finishings
fast hardening
Smooth rugged touch
Easy mixing
Do not come in clots

TECHNICAL CHARACTERISTICS

Referencia Color	
Mixture relation	450-550 ml de agua por kg masilla
Finish	Matt
Specific weight	2,42± 0,05 kg/l
Solids in volume	100± 1
Solids in weight	100± 1
Aproximated performance by coat	Depending of product usage
Dry to touch	(20°C HR: 60%): 4-5h
Dry to repaint	(20°C HR: 60%): 24-48h
Colours	White

SURFACE PREPAIRING

New surfaces

*-Cement / plaster mortar: Check suitability of PLASMONT MULTIUSO STANDARD on surface. -Allow to harden completely (minimum 30 days) -Remove possible efflorescence and neutralise alkaline surfaces. -Sand to open the pores of excessively polished surfaces.

-Remove external products and/or residues. -Back gouge any cracks or fissures down to repaired base, remove subsequent dust with brush and apply PLASMONT MULTIUSO STANDARD filler as instructed in the Application Systems and Applications. -Do not exceed the maximum recommended thickness of coats. - On surfaces in an excessively poor condition suitable fixative should be used before applying filler (see product family 6).

-Wood: -Check suitability of PLASMONT MULTIUSO STANDARD on surface. - Sand to open pores of excessively polished surfaces. -Remove external products and/or residues.

-Back gouge any cracks or fissures down to repaired base, remove subsequent dust with brush and apply PLASMONT MULTIUSO STANDARD filler as instructed in the Application Systems and Applications. -Do not exceed the maximum recommended thickness of coats. -Apply on healthy, grease-free, resin free, dust free and dry wood with less than 20% internal dampness. If the wood shows signs of ageing it should be sanded and the cracks back gouged to healthy wood.

Restoring and maintenance

Remove off any remains or chipping of product or any other foreign product. Open pore by sandpàpering or any other mechanical systems. Test adherence level and treat as per new surfaces.

WAY OF USE**Application notes**

Dilute with clean, unpolluted water.

Use the tools indicated in the application system instructions. Ensure the tools are clean, in good working order and of course, rust free.

Repaint following the indicated period of time. Given that this depends on the levels of humidity, temperature and thickness of the coating, the lack of clogging of the sandpaper with indicate that the product is ready for repainting.

Solvent for dilution and cleaning

Water

Way of use

Stainless trowel

Palette / spatula

Palette

Aproximate dilution

450-550 ml agua/kg masilla

450-550 ml de agua/kg masilla

450-550 ml de agua/kg masilla

SYSTEM**Procedures depending of surface type**

	Primer	Intermedium	Finish
Wood			
MAX	Selladora sellalux	Selladora sellalux	Fijador + Montoplástica o Familia 4
STD	Plasmont Multiusos Standar		Montoplástica o Familia 4
Project			
MAX	Fijador (Emulsión Fijadora Fijamont)	Plasmont Multiusos Standar	Fijador + Montoplástica, Familia 4
STD	Plasmont Multiusos Standar		Montoplástica, Familia 4

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE**PACKINGS**

1 Kg, 5 Kg, 15 Kg