

Fecha de Alta

25-06-2007

Versión

4 - 20/05/2024



FAMILY LINE

PREPARACIONES, FONDOS E IMPR.
MASILLAS EN POLVO

DESCRIPTION AND NATURE

Powdered filler for smoothing textured surfaces, can be applied in thick layers. Specially suitable for smoothing textured surfaces.

USAGES

Indoors
Plaster
Concrete
Plaster

PROPERTIES

Adherence
Optimal applicability
No flammable
Fast drying
High thickness coats
It fix very good over Matt Water Paintings
Easy sandable
Minimum decrease
Long open time
Maximum recommended thickness : 7mm

TECHNICAL CHARACTERISTICS

Referencia Color	PLASMONT RENOVACION
Finish	Matt
Specific weight	2,5± 0,05 kg/l
Solids in volume	100± 1
Solids in weight	100± 1
Aproximated performance by coat	Depending of product usage
Dry to touch	(20°C HR: 60%): 4-5h
Dry to repaint	(20°C HR: 60%): 24-48h
Colours	White

SURFACE PREPAIRING

New surfaces

Plaster and cement mortar:

- Test PLASMONT RENOVACION suitability on surface.
- Wait till complete drying of product (30 days).
- Remove off any efflorescences and neutralize alkaline surfaces.
- Extremely polished surfaces should be sandpapered to open pores.
- Remove off any foreign products or remains.
- Open any fissures or cracks until obtaining good condition surface. Remove off any resulting dust by brushing and apply PLASMONT RENOVACION as recommended under Application Systems and Application points.
- For extremely damaged surfaces, use suitable fixer (see family 6) before puttying.
- Recommended maximum thickness per coat should always be observed.

Fecha de Alta

25-06-2007

Versión

4 - 20/05/2024

Restoring and maintenance

Remove off any remains or chipping of product or any other foreign product. Open pore by sandpæpering or any other mechanical systems.

Test adherence level and treat as per new surfaces.

WAY OF USE**Application notes**

Use clean and rust-free tools detailed in the Application System.

Anchor adequately.

We usually recommend coats of between 5-7 mm at most.

Three or more coats can be applied to a thickness of up to 15 mm.

Repaint following the indicated period of time. Given that this depends on the levels of humidity, temperature and thickness of the coat, the lack of clogging of the sandpaper with indicate that the product is ready for repainting.

Suitable finishing products: Ovaldine, Montoplástica, Montonature, Esmalte Montosintético, Luxatín and High Decoration products.

Solvent for dilution and cleaning

Water

Way of use

Stainless trowel

Pallette / spatula

Aproximate dilution

400ml de agua por kg

400ml de agua por kg

SYSTEM**Procedures depending of surface type**

	Primer	Intermedium	Finish
New work			
MAX	Emulsión fijadora, Fijamont, Fijalite	Plasmont renovación	Montoplástica, Montonature, Ovaldine, Montosintetic, Luxatín, Alta decoración.
STD	Plasmont renovación	Emulsión fijadora, Fijamont	Montoplástica, Montonature, Ovaldine, Montosintetic, Luxatín, Alta decoración.
Plasterboard			
MAX	Plasmont renovación	Plasmont renovación	Montoplástica, Montonature, Ovaldine, Montosintético, Luxatín, Alta decoració.
STD	Plasmont renovación	Fijador (Emulsón fijadora, Fijamont	Montoplástica, Montonature, Ovaldine, Montosintético, Luxatín, Alta decoració.

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Fecha de Alta

25-06-2007

Versión

4 - 20/05/2024

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to establish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

5 Kg, 15 Kg

**FAMILY
LINE****DESCRIPTION AND NATURE**

Powdered filler for smoothing textured surfaces, can be applied in thick layers. Specially suitable for smoothing textured surfaces.

USAGES**PROPERTIES**

Adherence
Optimal applicability
No flammable
Fast drying
High thickness coats
It fix very good over Matt Water Paintings
Easy sandable
Minimum decrease
Long open time
Maximum recommended thickness : 7mm

TECHNICAL CHARACTERISTICS

Referencia Color

Finish Matt

Specific weight 2,5± 0,05 kg/l

Solids in volume 100± 1

Solids in weight 100± 1

Aproximated performance by coat Depending of product usage

Dry to touch (20°C HR: 60%): 4-5h

Dry to repaint (20°C HR: 60%): 24-48h

Colours White

SURFACE PREPAIRING

New surfaces

Plaster and cement mortar:

- Test PLASMONT RENOVACION suitability on surface.
- Wait till complete drying of product (30 days).
- Remove off any efflorescences and neutralize alkaline surfaces.
- Extremely polished surfaces should be sandpapered to open pores.
- Remove off any foreign products or remains.
- Open any fissures or cracks until obtaining good condition surface. Remove off any resulting dust by brushing and apply PLASMONT RENOVACION as recommended under Application Systems and Application points.
- For extremely damaged surfaces, use suitable fixer (see family 6) before puttying.
- Recommended maximum thickness per coat should always be observed.

Restoring and maintenance

Remove off any remains or chipping of product or any other foreign product. Open pore by sandpapering or any other mechanical systems.

Test adherence level and treat as per new surfaces.

WAY OF USE**Application notes**

Use clean and rust-free tools detailed in the Application System.

Anchor adequately.

We usually recommend coats of between 5-7 mm at most.

Three or more coats can be applied to a thickness of up to 15 mm.

Repaint following the indicated period of time. Given that this depends on the levels of humidity, temperature and thickness of the coat, the lack of clogging of the sandpaper with indicate that the product is ready for repainting.

Suitable finishing products: Ovaldine, Montoplástica, Montonature, Esmalte Montosintético, Luxatín and High Decoration products.

Solvent for dilution and cleaning

Water

Way of use

Stainless trowel

Pallette / spatula

Aproximate dilution

400ml de agua por kg

400ml de agua por kg

SYSTEM**Procedures depending of surface type**

	Primer	Intermedium	Finish
New work			
MAX	Emulsión fijadora, Fijamont, Fijalite	Plasmont renovación	Montoplástica, Montonature, Ovaldine, Montosintético, Luxatín, Alta decoración.
STD	Plasmont renovación	Emulsión fijadora, Fijamont	Montoplástica, Montonature, Ovaldine, Montosintético, Luxatín, Alta decoración.
Plasterboard			
MAX	Plasmont renovación	Plasmont renovación	Montoplástica, Montonature, Ovaldine, Montosintético, Luxatín, Alta decoración.
STD	Plasmont renovación	Fijador (Emulsión fijadora, Fijamont	Montoplástica, Montonature, Ovaldine, Montosintético, Luxatín, Alta decoración.


SECURITY

Fecha de Alta

25-06-2007

Versión

4 - 20/05/2024



Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE**PACKINGS**

5 Kg, 15 Kg