

Fecha de Alta

26-01-2009

Versión

5 - 23/05/2024



FAMILY LINE

PREPARACIONES, FONDOS E IMPR.
IMPRIMACIONES MADERA-OBRA

DESCRIPTION AND NATURE

Synthetic-based alkyd resins, for sealing porous surfaces that are to be finished with primer pigmented products.

USAGES

Outdoors/Indoors

Cement

Plaster

Iron

Wood

PROPERTIES

Penetration power
No sanding necessary for repainting. Non expensive maintenance
Good adhesion
Drying fast
Odourless when dry
Good applicability

TECHNICAL CHARACTERISTICS

Referencia Color	SELLADORA SELLALUX
Finish	Satin
Specific weight	1,49± 0,05 kg/l
Viscosity	194 +/- 30 SG
Solids in volume	40± 1
Solids in weight	75± 1
VOC	Cat. h/BD 750/750 (2007/2010): 475,52 g/l
Aproximated performance by coat	8-10 m²/L

Dry to touch	(20°C HR: 60%): 30-90min
Dry to repaint	(20°C HR: 60%): >24h
Colours	white

SURFACE PREPAIRING

New surfaces

Cement mortar, plaster and by products.

-Wait till complete drying of product (30 days minimum).

-Surface should be totally dry.

-Remove off any efflorescences and neutralize alkaline surfaces.

-Remove off any foreign products or remains.

-Cover surface imperfections with suitable plaster or putty (See Family 6 to help you choose the most suitable product to prepare surfaces).

-Mildewed surfaces should be treated with Montolimp.

-New wood:

-Only apply on wood with less than 12% moisture content.

-Sandpaper and eliminate any remains in joints and mechanical faults.

-Old wood should be previously sandpapered and primed. Remove any dust by brushing it off or using any other mechanical system.

Fecha de Alta

26-01-2009

Versión

5 - 23/05/2024

-Cover surface imperfections with plaster or putty (See Family 6 to help you choose the most suitable product to prepare surfaces).

-We recommend applying Anticarcomas Klearxyl Di due to its fungicidal action.

Iron and steel:

-Remove off any rust by abrasive blast cleaning before finishing coat application.

-Paint, primer and pre-treatment are equally important.

-If abrasive blast cleaning is not possible, remove off any rust by brushing, sandpapering or any other mechanical system. Any old rust can also be treated by applying our Oxifin (ref. 1900).

Restoring and maintenance

Iron and its enamelled by-products:

-Any Foreign products, grease or rust should be removed following indications as per new surfaces.

Painted wood and construction (plaster, cement, and by products):

-If they have been varnished with Montoxyl, remove off foreign products and areas in bad condition, sandpaper slightly, remove resulting dust and treat as per new wood.

-If they have been varnished, apply a stripping product such as Quitamont Universal (ref. 3510) or use a mechanical system and proceed as per new wood.

WAY OF USE

Application notes

-Stir product thoroughly.

-Follow application guidelines shown on table below.

-Do not apply product at high temperatures or overheated surfaces exposed to sunshine.

-Keep room well ventilated while product is drying.

-Do not apply when moisture contents is over 80%.

Solvent for dilution and cleaning

Solvent 1401, 1402

Way of use	Aproximate dilution
Painting brush	5-15%
Roller	5-15%
Air-less gun	20-30%
Air-mix gun	20-30%
Aerographic gun	20-30%
Low pressure turbo	20-30%

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Metal decoration			
MAX			
STD	Selladora Sellalux	Selladora Sellalux	Montosintético, Luxatín, Marisma, Ferrum
New work			
MAX	Selladora Sellalux	Selladora Sellalux	Montosintético, Luxatín, Marisma, Ferrum
STD	Fijamont, Emulsión Fijadora		Montoplástica, Ovaldine, Montonature
New wood indoor/outdoor			
MAX	Anticarcomas Klearxyl Di	Selladora/Sellalux	Montosintético, luxatín, marisma, Ferrum
STD	Selladora/Sellalux		Montoplástica, Ovaldine, Montonature

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

0.375 L, 0.75 L, 4 L