

Fecha de Alta

30-03-2007

Versión

14 - 20/08/2024



FAMILY MADERA

LINE PROTECTORES (AGUA)

DESCRIPTION AND NATURE

Acrylic-urethane water-based primer. Excellent brushability, odourless. Great adhesion and excellent whiteness and coverage. Great filling capacity and easy to sand.

USAGES

Outdoors/Indoors

Cement

Plaster

Wood

PROPERTIES

Penetration power
 No sanding necessary for repainting. Non expensive maintenance
 Good adhesion
 Drying fast
 Odourless when dry
 Good applicability

TECHNICAL CHARACTERISTICS

Referencia Color	SELLADORA ACQUA BLANCA
Finish	Satin
Specific weight	1,44± 0,05 kg/l
Viscosity	45 +/- 5 PO
Solids in volume	38± 1
Solids in weight	58± 1
VOC	Cat. d/BA 150/130 (2007/2010): 49,09 g/l
Aproximated performance by coat	7-10 m ² /L
Dry to touch	(20°C HR: 60%): 1-2h
Dry to repaint	(20°C HR: 60%): >24h
Colours	White

SURFACE PREPAIRING

New surfaces

- Cement mortar, plaster and their derivatives:
- Wait until completely set (30 days minimum).
- Wait until they are very dry.
- The support must be free of foreign products and/or residues.
- Clean the support of possible efflorescence, as well as neutralize alkaline surfaces.
- Putty any possible damage to the support with suitable putty (See in the BACKGROUND REPAIR family the lines corresponding to powder plasters and prepared putties to make an appropriate choice).
- Treat moldy supports with Montolimp.

New woods:

- On the outside, protect the wood with Klearxyl Di Antiworms from attack by fungi and xylophagous insects.
- Apply to wood with a moisture content of less than 12%.
- Sand and eliminate possible traces of glue in the assemblies and machining errors.

Fecha de Alta

30-03-2007

Versión

14 - 20/08/2024

-If the wood shows signs of aging, it must be previously sanded and dust removed by brushing or any other mechanical means.

Restoring and maintenance

- Painted wood and work (plaster, cement and derivatives).

-On wood varnished with Montoxyl, remove foreign products, eliminate poorly adhered areas or areas in poor condition, sand lightly, remove the dust resulting from sanding and proceed as with new wood.

-If they have been varnished, remove them by stripping or using mechanical means and proceed as with new wood.

-On the outside, protect the wood with Klearxyl Di Antiworms from attack by fungi and xylophagous insects.

WAY OF USE

Application notes

Stir the product until it is perfectly homogenized.

Apply following the rules marked in the attached application table.

Do not apply the product at high temperatures, or on surfaces exposed to strong sunlight.

Maintain good ventilation conditions during drying time.

Do not apply with relative humidity greater than 80%.agos.

Solvent for dilution and cleaning

Water

Way of use	Aproximate dilution
Painting brush	0-10%
Roller	0-10%
Air-less gun	10-30%
Air-mix gun	10-30%

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
New work			
MAX	Selladora Acqua	Selladora Acqua	Familia 1, 2 y 4 excepto acabados de 2 componentes
STD	Selladora Acqua		Familia 1, 2 y 4 excepto acabados de 2 componentes
New wood indoor/outdoor			
MAX	Al exterior: Anticarcomas Klearxyl Di	Selladora Acqua	Familia 1, 2 y 4 excepto acabados de 2 componentes, familia 5 al agua, Montoxyl Lasure Acqua Acabado pigmentado
STD	Al exterior: Anticarcomas Klearxyl Di	Selladora Acqua	Familia 1, 2 y 4 excepto acabados de 2 componentes, familia 5 al agua, Montoxyl Lasure Acqua Acabado pigmentado

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C.

For further information, please check product safety sheet.

Fecha de Alta

30-03-2007

Versión

14 - 20/08/2024

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to establish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

0.75 L, 4 L