

Fecha de Alta

24-12-2020

Versión

4 - 16/01/2025



FAMILY LINE

REVESTIMIENTOS DE FACHADAS / SISTEMAS TINTOMÉTRICOS
RUGOSOS

DESCRIPTION AND NATURE

Rough coating for protection and decoration of façades and exterior walls. The texture allows hiding defects. Good durability and resistance to sunlight (UV) and rainwater.

Ideal for professional application: high coverage, high performance, low gloss and fast execution.

USAGES

Outdoors/Indoors

Facades

Concrete

Cement mortars

Porous brick

PROPERTIES

Water vapor permeability: V2 (very breathable) (according to UNE-EN 1062-1 standard)

Dry film thickness: E5 (< 400 microns, according to standard 1062-1)

The product can be guaranteed for up to 7 years for white and 5 for COF and FE, see conditions

Permeability to liquid water: W3 (maximum impermeability) (according to UNE-EN 1062-1 standard)

TECHNICAL CHARACTERISTICS

Referencia Color	MONTOKRIL TEXTURADO BLANCO
Finish	Textured
Specific weight	1,57 ± 0,05 kg/l
Viscosity	150 +/- 10 PO
Solids in volume	49 ± 1
Solids in weight	69 ± 1
VOC	Cat. c/BA 75/40 (2007/2010): 1,42 g/l
Aproximated performance by coat	6-9 m ² /L
Dry to touch	(20°C HR: 60%): 1h
Dry to repaint	(20°C HR: 60%): 4-6h
Colours	Bases: BL, IN, TR White 103 and colors of COF and FACHADAS ETERNA Tintometric Systems.

SURFACE PREPAIRING

French norm DTU 59.1

New surfaces

Concrete and cement mortars:

1. Wait until fully set 30 days minimum
2. Clean the surface of possible efflorescence via abrasive blasting
3. Neutralise alkaline surfaces.
4. On polished surfaces, sand to create a rougher surface.
5. Clean the surface to remove foreign products.
6. Fix crumbly surfaces with a suitable fixative (Fijamont or Fixing Emulsion).
7. Use putty on surface defects (Elastic or Plasmont Exterior or Montó equivalent).

Porous bricks:

1. Remove any cracks, holes or irregularities with Plasmont Exterior or Montó equivalent.

Fecha de Alta

24-12-2020

Versión

4 - 16/01/2025

2. Clean the surface before painting.

3. It is advisable to apply a primer before painting due to the porosity of the brick, thus avoiding wasting paint.

Restoring and maintenance

1. On painted surfaces, check that the paint is solid and well-adhered. Its condition must be assessed, in order to avoid possible incompatibilities. Dust and dirt must also be eliminated before repainting.

2. Completely remove old paint that is in poor condition or that is poorly-adhered.

3. Treat mouldy surfaces with Monto Limpia Moho.

4. Glossy surfaces should be thinned out to ensure good adhesion.

5. Putty the surface defects with exterior filler (see the corresponding powder fillers and ready-mixed fillers in the SURFACE PREPARATION product range to make the right choice).

WAY OF USE**Application notes**

- Do not apply the product at temperatures below 5°C C or above 35°C or with imminent risk of rain.

- Do not apply in full sun or on excessively humid days.

- Shake the product until it is perfectly homogenised.

- For the first coat, dilute the product according to the porosity and state of the surface.

- Finish with one or more lightly diluted coats until the surface is completely covered.

Solvent for dilution and cleaning

Water

Way of use

Painting brush

Roller

Aproximate dilution

10-20%

10-20%

SYSTEM**Procedures depending of surface type**

	Primer	Intermedium	Finish
Support with mould			
MAX	Limpiar + Monto Limpia Moho + Montokril Texturado diluido	Montokril Texturado	Montokril Texturado
STD	Limpiar + Monto Limpia Moho + Montokril Texturado diluido		Montokril Texturado
Masonry mortar			
MAX	Fijamont, Emulsión Fijadora	Montokril Texturado	Montokril Texturado
STD	Montokril Texturado diluido		Montokril Texturado Liso
Old paintings in bad state			
MAX	Eliminar + Fijamont, Emulsión Fijadora	Montokril Texturado	Montokril Texturado
STD	Eliminar + Montokril Texturado diluido		Montokril Texturado
Support weak			
MAX	Fijamont, Emulsión Fijadora	Montokril Texturado	Montokril Texturado
STD	Montokril Texturado diluido		Montokril Texturado
Old paintings in good condition			
MAX	Montokril Texturado diluido	Montokril Texturado	Montokril Texturado
STD	Montokril Texturado diluido		Montokril Texturado

Fecha de Alta

24-12-2020

Versión

4 - 16/01/2025

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

4 L, 12 L