

Fecha de Alta

24-12-2020

Versión

5 - 16/01/2025



FAMILY
LINE

REVESTIMIENTOS DE FACHADAS / SISTEMAS TINTOMÉTRICOS
LISOS 100% ACRILICOS

DESCRIPTION AND NATURE

Smooth elastic coating for protection and decoration of façades and exterior walls. Highly durable and resistant: sunlight (UV), extreme temperatures, rainwater, environmental dirt, microorganisms and mould, chalk, colour degradation, carbonation of concrete, paint ageing.

Ideal for professional application: high coverage, high performance, low gloss and fast execution. This product contributes to LEED®, BREEAM® and VERDE certifications.

USAGES

Outdoors/Indoors

Facades

Concrete

Cement mortars

Porous brick

PROPERTIES

Washability: Class 1 (according to Standard UNE-EN 13300)

With anti-mould additive

Gloss level: extra matt (according to 13300 standard, at 85° reflectance <5)

Water vapor permeability: V2 (very breathable) (according to UNE-EN 1062-1 standard)

The product can be guaranteed for up to 12 years for white and 10 for COF and FE, see conditions

CE Marked (UNE-EN 1504-2)

Dry film thickness: E2 (between 50 and 100 microns, according to standard UNE-EN 1062-1) calculated for an average yield of approximately two coats for white (see Technical Characteristics). This information may vary depending on the colour chosen.

Crack resistance certificate according to UNE-EN 10627 standard: A3 (23°C). Absorbs micro-cracks up to 0.5 mm.

Opacity: Class 1 for white (according to Standard UNE-EN 13300). This information may vary depending on the colour chosen.

Gloss: G3 (matt, according to the UNE-EN 1062-1 standard)

Permeability to liquid water: W3 (maximum impermeability) (according to UNE-EN 1062-1 standard)

Carbon dioxide permeability: C1 (anti-carbonation) (according to UNE-EN 1062-1)



TECHNICAL CHARACTERISTICS

Referencia Color	OVALDINE ANTIFISURAS BLANCO
Finish	Smooth matt
Specific weight	1,48± 0,05 kg/l

Fecha de Alta

24-12-2020

Versión

5 - 16/01/2025

Viscosity	130 +/- 10 PO
Solids in volume	54± 1
Solids in weight	70± 1
VOC	Cat. c/BA 75/40 (2007/2010): 16,01 g/l
Aproximated performance by coat	10-12 m²/L
Dry to touch	(20°C HR: 60%): 1h
Dry to repaint	(20°C HR: 60%): 4-6h
Colours	Bases: BL, IN, TR White 103 and colors of COF and FACHADAS ETERNA

SURFACE PREPAIRING

French norm DTU 59.1

New surfaces

Concrete and cement mortars:

1. Wait until fully set 30 days minimum
2. Clean the surface of possible efflorescence via abrasive blasting
3. Neutralise alkaline surfaces.
4. On polished surfaces, sand to create a rougher surface.
5. Clean the surface to remove foreign products.
6. Fix crumbly surfaces with a suitable fixative (Fijamont or Fixing Emulsion).
7. Use putty on surface defects (Elastic or Plasmont Exterior or Montó equivalent).

Porous bricks:

1. Remove any cracks, holes or irregularities with Plasmont Exterior or Montó equivalent.
2. Clean the surface before painting.
3. It is advisable to apply a primer before painting due to the porosity of the brick, thus avoiding wasting paint.

Restoring and maintenance

1. On painted surfaces, check that the paint is solid and well-adhered. Its condition must be assessed, in order to avoid possible incompatibilities. Dust and dirt must also be eliminated before repainting.
2. Completely remove old paint that is in poor condition or that is poorly-adhered.
3. Treat mouldy surfaces with Monto Limpia Moho.
4. Glossy surfaces should be thinned out to ensure good adhesion.
5. Putty the surface defects with exterior filler (see the corresponding powder fillers and ready-mixed fillers in the SURFACE PREPARATION product range to make the right choice).

WAY OF USE

Application notes

- Do not apply the product at temperatures below 5°C C or above 35°C or with imminent risk of rain.
- Do not apply in full sun or on excessively humid days.
- Shake the product until it is perfectly homogenised.
- For the first coat, dilute the product according to the porosity and state of the surface.
- Finish with one or more lightly diluted coats until the surface is completely covered.

Solvent for dilution and cleaning

Water

Way of use	Aproximate dilution
Painting brush	10-20%
Roller	10-20%
Air-less gun	10-30%
Air-mix gun	10-30%
Aerographic gun	10-30%
Low pressure turbo	10-30%

Fecha de Alta

24-12-2020

Versión

5 - 16/01/2025

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Support with mould			
MAX	Limpiar + Monto Limpia Moho + Ovaldine Antifisuras diluíe	Ovaldine Antifisuras	Ovaldine Antifisuras
STD	Limpiar + Monto Limpia Moho + Ovaldine Antifisuras diluíe		Ovaldine Antifisuras
Masonry mortar			
MAX	Fijamont, Emulsión Fijadora	Ovaldine Antifisuras	Ovaldine Antifisuras
STD	Ovaldine Antifisuras diluíe		Ovaldine Antifisuras
Old paintings in bad state			
MAX	Eliminar + Fijamont, Emulsión Fijadora	Ovaldine Antifisuras	Ovaldine Antifisuras
STD	Eliminar + Ovaldine Antifisuras diluíe		Ovaldine Antifisuras
Support weak			
MAX	Fijamont, Emulsión Fijadora	Ovaldine Antifisuras	Ovaldine Antifisuras
STD	Ovaldine Antifisuras diluíe		Ovaldine Antifisuras
Old paintings in good condition			
MAX	Ovaldine Antifisuras diluido	Ovaldine Antifisuras	Ovaldine Antifisuras
STD	Ovaldine Antifisuras diluido		Ovaldine Antifisuras

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in drain. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to establish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

4 L, 12 L