

MONTOSPRAY ANTICALORICO



FAMILY

ESMALTES

LINE

SPRAY MULTISOPORTE

DESCRIPTION AND NATURE

Spray enamel designed to withstand temperatures up to 600°C

USAGES

Cement
Plaster
Brick
Stone
Iron
steel

PROPERTIES

Adherence
Resistance to the chemical attacks
Fast drying
Good coverage
Strong resistance to the atmospherical factors
Odourless when dry

TECHNICAL CHARACTERISTICS

Referencia Color	MONTOSPRAY ANTICALORICO NEGRO
Aproximated performance by coat	Depending of product usage

Dry to touch	15min
Dry to repaint	24h
Colours	Black 904 and Silver 906

SURFACE PREPAIRING

New surfaces

Iron, derived metals and other metals

- The surface must be free of foreign products and/or residues.
- The surface must be degreased, clean and dry.
- On rusty surfaces, we must eliminate the rust by the usual means recommended by Montó with any rust inhibitor manufactured by our Company, which should be applied in advance.
- We must protect the areas that we do not want to paint.
- Eliminate, in general, products that are poorly adhered or in poor condition

Works (plaster, cement and derivatives, cardboard):

- Eliminate foreign products and/or residues.
- The surface must be degreased, clean and dry.
- Eliminate possible efflorescence using traditional methods.
- Eliminate, in general, products that are poorly adhered or in poor condition.

Restoring and maintenance

Clean and proceed as with new surfaces.

MONTOSPRAY ANTICALORICO

WAY OF USE

Application notes

Shake the container vigorously for about 2 minutes to homogenise its contents perfectly.

Carry out application tests in a non-visible place.

Protect areas that are not to be painted.

Apply at a distance of 25-30cm from the surface in light, criss-cross strokes.

Do not apply the product at high temperatures, or on surfaces exposed to strong sunlight.

Maintain good ventilation conditions during the drying time.

Do not apply while the relative humidity is above 80%.

Do not use at temperatures below 15°C.

When finished, empty the contents of the cannula by dosing with the container upside down.

Before lighting the stove or heating the painted surface, let it dry for a minimum of 48 hours.

Approximate yield per 400ml container 1 - 2 m2 (two cross-coats)

Solvent for dilution and cleaning

Solvent 1406-05

Way of use

Aproximate dilution

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Metal			
MAX	Montospray Anticalórico	Montospray Anticalórico	Montospray Anticalórico
STD	Montospray Anticalórico		Montospray Anticalórico

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water.

Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C.

For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 48 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to establish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

0.4 L