

Fecha de Alta

09-12-2022

Versión

3 - 06/05/2024



**FAMILY**  
**LINE**

ESMALTES / SISTEMAS TINTOMÉTRICOS

POLIURETANOS MULTISOORTE

**DESCRIPTION AND NATURE**

Two component aliphatic polyurethane varnish, acrylic-based in a solvent medium, for direct application on any support or on supports properly prepared on polyurethanes or MONTÓ epoxies.

**USAGES**

Outdoors/Indoors

Metal

Construction

Iron

Galvanized iron

Wood

**PROPERTIES**

Does not turn yellow

Optimal applicability

Do not crack

Strongness

Elasticity

Makes a film

Do not blister

Levelling

Resistance to friction and hits

UV filters

Chemical resistance

Good yield

Good applicability

**TECHNICAL CHARACTERISTICS**

Referencia Color	BARNIZ ACRIPOL MATE
Mixture relation	4 Acripol, 1 Cat. en volumen
Finish	Matt
Specific weight	1,03± 0,05 kg/l
Viscosity	120 +/- 20 SG
Solids in volume	43± 1
Solids in weight	52± 1
VOC	Cat. j/BD 550/500 (2007/2010): 487,13 g/l
Aproximated performance by coat	10-15 m²/L

Dry to touch	(20°C HR: 60%): 30-60min
Dry to repaint	12-24h
Colours	Transparent

**SURFACE PREPAIRING****New surfaces**

Iron and by-products:

- For surface protection prior to decoration, apply a suitable primer (see family 6) following its corresponding data sheet guidelines.

Fecha de Alta

09-12-2022

Versión

3 - 06/05/2024

-Prior to decoration, surface should be free of any foreign products, grease, dust and completely dry. Should it show any rust, apply our Oxifin or remove it by brushing it off or any other mechanical system.

New wood:

- Surface should be free of any foreign products or remains.
- Apply on wood with less than 20% moisture content.
- Apply on wood in good condition, dry and free of grease and dust.
- Sandpaper and eliminate any remains in joints and mechanical faults.
- Old wood should be previously sandpapered and primed. Remove any dust by brushing it off or using any other mechanical system.
- We recommend priming with GAMA MONTOPOL FONDO.

Construction (plaster, cement and by-products):

- Remove off any efflorescences and neutralize alkaline surfaces.
- Remove off any foreign product or remains.
- Once dry, prime with with the same diluted product.

### Restoring and maintenance

Iron and its enamelled by-products:

- For paints in good condition, sandpaper slightly to open pore and test adherence level.
- Paints in bad condition should be removed by mechanical or chemical systems and proceed as per new surfaces.

Painted or varnished wood:

- If they have been varnished with Montoxyl Colour (ref. 1300), remove off foreign products and areas in bad condition, sandpaper slightly, remove resulting dust and treat as per new wood.
- If they have been varnished, apply a stripping product such as Quitamont Universal (ref. 3510) or use a mechanical system and proceed as per new wood.

Construction (plaster, cement and by-products):

- For paint in good condition, sandpaper slightly to open pore and test adherence level.
- For paints in bad condition, or paints that could be damaged by the product, remove them off by mechanical or chemical systems and proceed as per new construction materials.

## WAY OF USE

### Application notes

- Mix both products Acripol Barniz + Catalizador and stir them until perfectly homogenized.
- Mixture should be obtained by pouring Catalizador (catalyst) over base (Acripol Barniz) (varnish) within given proportions.
- Do not apply with relative humidity above 80%, or at temperatures below 5°C.
- Do not apply the product at high temperatures, or on surfaces exposed to strong sunlight.
- Keep room well ventilated while product is drying.
- Given the wide spectrum of supports in direct applications on difficult-to-adhere surfaces, it is convenient to carry out technical adhesion tests.
- When pore is open, apply the priming products shown in table below.
- The previously stated performance information refers to the CA+CB mix

### Solvent for dilution and cleaning

polyurethane 1410, 1406

#### Way of use

Aerographic gun

Brush, roller or spray gun

#### Aproximate dilution

Al uso

Al uso

## SYSTEM

### Procedures depending of surface type

	Primer	Intermedium	Finish
<b>Iron, steel,</b>			
<b>MAX</b>	Impripol o Barniz Acripol mate diluido	Impripol o Barniz Acripol mate diluido	Barniz Acripol mate
<b>STD</b>	Impripol o Barniz Acripol mate diluido		Barniz Acripol mate

### Work indoors / outdoors

<b>MAX</b>	Barniz Acripol brillo diluido	Barniz Acripol mate diluido	Barniz Acripol mate
------------	-------------------------------	-----------------------------	---------------------

Fecha de Alta

09-12-2022

Versión

3 - 06/05/2024

<b>STD</b>	Barniz Acripol brillo diluido		Barniz Acripol mate
<b>Galvanised iron</b>			
<b>MAX</b>	Impripol o Barniz Acripol mate diluido	Impripol o Barniz Acripol mate diluido	Barniz Acripol mate
<b>STD</b>	Barniz Acripol mate diluido		Barniz Acripol mate
<b>Wood</b>			
<b>MAX</b>	Montopol fondo	Montopol fondo o Barniz Acripol mate diluido	Barniz Acripol
<b>STD</b>	Montopol fondo o Barniz Acripol mate diluido		Barniz Acripol

## SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

## NOTE

Maximum recommended storage time : 12 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

## PACKINGS

0.6 L  
Canned bases 3.2 L



## FAMILY LINE

## DESCRIPTION AND NATURE

Two component aliphatic polyurethane varnish, acrylic-based in a solvent medium, for direct application on any support or on supports properly prepared on polyurethanes or MONTÓ epoxies.

## USAGES

## PROPERTIES


Does not turn yellow  
Optimal applicability  
Do not crack  
Strongness  
Elasticity  
Makes a film

Fecha de Alta

09-12-2022

Versión

3 - 06/05/2024



Do not blister  
 Levelling  
 Resistance to friction and hits  
 UV filters  
 Chemical resistance  
 Good yield  
 Good applicability

## TECHNICAL CHARACTERISTICS

Referencia Color	
Mixture relation	4 Acipol, 1 Cat. en volumen
Finish	Matt
Specific weight	1,03± 0,05 kg/l
Viscosity	120 +/- 20 SG
Solids in volume	43± 1
Solids in weight	52± 1
VOC	Cat. j/BD 550/500 (2007/2010): 487,13 g/l
Aproximated performance by coat	10-15 m²/L
Dry to touch	(20°C HR: 60%): 30-60min
Dry to repaint	12-24h
Colours	Transparent

## SURFACE PREPAIRING

### New surfaces

Iron and by-products:

- For surface protection prior to decoration, apply a suitable primer (see family 6) following its corresponding data sheet guidelines.

-Prior to decoration, surface should be free of any foreign products, grease, dust and completely dry. Should it show any rust, apply our Oxifin or remove it by brushing it off or any other mechanical system.

New wood:

-Surface should be free of any foreign products or remains.

-Apply on wood with less than 20% moisture content.

-Apply on wood in good condition, dry and free of grease and dust.

-Sandpaper and eliminate any remains in joints and mechanical faults.

-Old wood should be previously sandpapered and primed. Remove any dust by brushing it off or using any other mechanical system.

-We recommend priming with GAMA MONTOPOL FONDO.

Construction (plaster, cement and by-products):

-Remove off any efflorescences and neutralize alkaline surfaces.

-Remove off any foreign product or remains.

-Once dry, prime with with the same diluted product.

### Restoring and maintenance

Iron and its enamelled by-products:

-For paints in good condition, sandpaper slightly to open pore and test adherence level.

-Paints in bad condition should be removed by mechanical or chemical systems and proceed as per new surfaces.

Painted or varnished wood:

-If they have been varnished with Montoxyl Colour (ref. 1300), remove off foreign products and areas in bad condition, sandpaper slightly, remove resulting dust and treat as per new wood.

- If they have been varnished, apply a stripping product such as Quitamont Universal (ref. 3510) or use a mechanical system and proceed as per new wood.

Construction (plaster, cement and by-products):

-For paint in good condition, sandpaper slightly to open pore and test adherence level.

-For paints in bad condition, or paints that could be damaged by the product, remove them off by mechanical or chemical systems and proceed as per new construction materials.

## WAY OF USE

## Application notes

- Mix both products Acripol Barniz + Catalizador and stir them until perfectly homogenized.
- Mixture should be obtained by pouring Catalizador (catalyst) over base (Acripol Barniz) (varnish) within given proportions.
- Do not apply with relative humidity above 80%, or at temperatures below 5°C.
- Do not apply the product at high temperatures, or on surfaces exposed to strong sunlight.
- Keep room well ventilated while product is drying.
- Given the wide spectrum of supports in direct applications on difficult-to-adhere surfaces, it is convenient to carry out technical adhesion tests.
- When pore is open, apply the priming products shown in table below.
- The previously stated performance information refers to the CA+CB mix

## Solvent for dilution and cleaning

polyurethane 1410, 1406

## Way of use

Aerographic gun

Brush, roller or spray gun

## Approximate dilution

Al uso

Al uso

## SYSTEM

## Procedures depending of surface type

	Primer	Intermedium	Finish
<b>Iron, steel,</b>			
<b>MAX</b>	Impripol o Barniz Acripol mate diluido	Impripol o Barniz Acripol mate diluido	Barniz Acripol mate
<b>STD</b>	Impripol o Barniz Acripol mate diluido		Barniz Acripol mate
<b>Work indoors / outdoors</b>			
<b>MAX</b>	Barniz Acripol brillo diluido	Barniz Acripol mate diluido	Barniz Acripol mate
<b>STD</b>	Barniz Acripol brillo diluido		Barniz Acripol mate
<b>Galvanised iron</b>			
<b>MAX</b>	Impripol o Barniz Acripol mate diluido	Impripol o Barniz Acripol mate diluido	Barniz Acripol mate
<b>STD</b>	Barniz Acripol mate diluido		Barniz Acripol mate
<b>Wood</b>			
<b>MAX</b>	Montopol fondo	Montopol fondo o Barniz Acripol mate diluido	Barniz Acripol
<b>STD</b>	Montopol fondo o Barniz Acripol mate diluido		Barniz Acripol

## SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

503516


# BARNIZ ACRIPOL MATE

Fecha de Alta

09-12-2022

Versión

3 - 06/05/2024



## NOTE

## PACKINGS

0.6 L

Canned bases 3.2 L